



Salmon Fields, Royton, Oldham, OL2 6HZ, England.
Tel: 0161 627 0101 Fax: 0161 627 0971.
web: www.jamesbriggs.co.uk

PRODUCT INFORMATION SHEET

VC41 DRY LUBE WITH PTFE

Reference 000103077571; Amendment 0, March 2008

1 Introduction

VC41 Dry Lube with PTFE is a pure PTFE spray designed to deposit an inert, dry film, low friction surface, effective over a wide service temperature range.

2. Where to Use

Suitable for all substrates including wood, metals, rubbers and plastics, and is particularly beneficial in the assembly/disassembly of pre-treated components.

3. Where not to use

- On any surface where application of a slippery film may create a health hazard.

4. Benefits

- Extremely fast drying
- Completely inert.
- Outstanding chemical resistance.
- Outstanding light resistance
- Exceptional thermal stability
- Non-greasy dry film does not attract airborne dirt and grit.
- Lowest coefficient of friction of all lubricants.

5. Physical Properties [Lubricant base except where stated]

Appearance	An opaque, non-homogeneous milky liquid
pH	Not applicable
Specific Gravity	0.700 +/- 0.15 @ 20°C
Non Volatiles % m/m, as supplied	5.0 – 7.5
Active Content % m/m, as supplied	20 - 30
Consistency	Free flowing liquid.
Flammability, as supplied	Extremely flammable, flash point below -20°C.
Composition Data, as supplied	A dispersion of PTFE in isopropanol, and naphtha [petroleum], hydrotreated, light, in a butane/isobutane/propane propellant.
Service Temperature [Continuous]	Up to 250°C
Service Temperature [Intermittent]	Up to 300°C

6. Application Details

Shake can thoroughly before use. Hold upright, and spray from a distance of 15 to 30cm. taking care to avoid overspray, especially on floors.

7. Availability

400 ml. aerosols

This information is provided in good faith based upon data and sources believed to be reliable and correct. Conditions of use, outside the control of the Company, dictate that no responsibility can be assumed for the ultimate performance of this product.